






6365 Black Tea




6366 Parsley




6367 Bahamas




6368 Chutney




6374 Pansy




6370 Silver and Gold




6371 Blueprint



6372 Sour Cherry



6373 Chestnut



6369 Quicksilver

Thicket

PERFORMANCE FABRIC

Grade Standard

Performance Summary

- Enhanced soil + stain resistance
- Enhanced abrasion resistance

Cleaning and Maintenance

Cleaning Code: **(W-S)** For water-based stains use water-based cleaners. For oil-based stains use solvent-based cleaners. We recommend using a professional cleaning service.

For additional cleaning information visit cfstinson.com

For complete specifications visit cfstinson.com

Dye lots may vary slightly.

*This term and any corresponding data refer to the typical performance in the tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.

Specifications



Content	60% Olefin, 40% Polyester
Finish	Non-PFOA Stain Resistant
Backing	Acrylic
Weight	9.0 oz./lin. yd. ± 1.0 oz.
Width	54 inches
Repeat	Horizontal: 2.75 inches, Vertical: 4.875 inches, directional

Performance Characteristics

Abrasion Resistance ASTM D-3597	Exceeds 70,000 double rubs - heavy duty
Break Strength ASTM D-5034	Warp: 111.0 lbs. min., Fill: 212.0 lbs. min.
Seam Slippage ASTM D-434	Warp: 61 lbs. min., Fill: 68.3 lbs. min.
Brush Pilling ASTM D-3511	Class 5.0 min.
Colorfastness to Light AATCC-16	40 Hours, Class 5.0
Crocking AATCC-8	Dry: Class 5.0, Wet: Class 5.0

Flammability*

California Technical Bulletin 117-2013 Section 1	Passed
UFAC	Class 1
NFPA 260	Class 1

May contribute to compliance with California Technical Bulletin 133 when used in conjunction with other suitable components.



2420 Long Lake Road
Roseville, MN 55113-7133

Phone: 651-361-7500
Phone: 1-800-MINNCOR (646-6267)

www.minncor.com

To place an order for a sample,
please contact MINNCOR at 651-361-7500
or email customer-service@minncor.com



C.F. Stinson, LLC
2849 Product Drive
Rochester Hills, MI 48309

P 800 841 6279
F 248 299 3884

cfstinson.com